

Macroplexx®

structural adhesives

TDS 5030

General Description

MACROPLEXX® 5030 is a high strength, two-part structural adhesive system, designed to offer extended open time for larger and more complex assemblies. On application, the grade's high viscosity is ideal for both gap filling and vertical surface applications. This unique Methacrylate chemistry can offer excellent tensile and impact strength, even without priming the surfaces. In addition, the advanced macro structure provides the bonded assembly with excellent environmental and chemical resistance in the most demanding applications.

Typical Applications

Automotive Panel Fabrication	Turbine Manufacture	Marine Stringer Assembly	GRP Tank Assembly
Vehicle Re-fitters	Horsebox Manufacture		

Chemical Resistance

Excellent Resistant to:

- Hydrocarbons
- Acids and Bases (3-10 ph)
- Salt Solutions

Packaging

- 25ml Syringe
- 50ml Cartridge
- 250ml Universal
- 400ml Cartridge
- Bulk Dispensing Systems

Physical Appearance

Adhesive Part A

Chemical Type	Methyl Methacrylate
Appearance	Off White Gel
Specific Gravity	0.97 (approx)
Viscosity @20°C mPa·s	
Brookfield Helipath	130,000 to 150,000
Flash Point	11°C

Activator Part B

Chemical Type	Methyl Methacrylate
Appearance	Amber/Yellowish Gel
Specific Gravity	0.95 (approx)
Viscosity @20°C mPa·s	
Brookfield Helipath	150,000 to 180,000
Flash Point	11°C

Mixture A&B

Appearance	Opaque Gel
Specific Gravity	0.97 (approx)
Viscosity @20°C mPa·s	
Brookfield Helipath < 4Min	150,000 to 200,000
Mix Ratio By Weight	1:1
Mix Ratio By Volume	1:1
Working Time 10g Mass	10-12 Minutes
Working Time in Nozzle	12 Minutes
Fixture time Steel @ 20°C	18-20 Minutes

Typical Properties Cured Material

Hardness ASTM Shore D	73
Shrinkage (7 days)	5%
Elongation at break	3%
Typical Handling Strength	2-4 Hours (Heavy Duty)

ASTM D1002 Lap Shears (Tensile Result)

Steel/steel	Up to 30 N/mm ²
Aluminium/aluminium	Up to 27 N/mm ²
Polycarbonate *	Up to 13 N/mm ²
On ABS/ABS *	Up to 8 N/mm ²

* Substrate failure

Suitable Substrates

ABS	Styrenes	Steel	Gelcoats
Acrylics	Urethanes	Aluminium	Polyesters
GRP	Vinyl	St. Steel	PVC
FRP	Carbon Fibre		

Application Instruction

Please consult Macroplexx application manual.

Terminology

(1) Working/Open Time: The time interval between application of adhesive to substrate, and the possible assembly/repositioning of the two mating parts @ 20°C

(2) Fixture Time: The length of time after the substrate assembly that will allow a joint to support a 1kg dead weight. (Tested on a 12mm x 25mm overlapped joint @ 20°C)



TDS 5030-5/6/2007

Portobello Industrial Estate, Birtley, County Durham, United Kingdom, DH3 2RE **Tel:** +44 (0)191 411 3191 **Fax:** +44 (0)191 411 3192

E-mail: info@holdtite.com **Web:** www.holdtite.com

The information contained herein is produced in good faith and is believed to be reliable but is for guidance only. Holdtite and its agents cannot assume liability or responsibility for results obtained in the use of its products by persons whose methods are outside or beyond our control. It is the users responsibility to determine the suitability of any of the products and methods of use or preparation prior to use mentioned in our literature and furthermore the users responsibility to observe and adopt such precautions as may be advisable for the protection of personnel and property in the handling and use of any of our products.

Last Revision 19-03-07